

## **Product data sheet**

## **Rigips pattressing**



Product description: Pattressing board, incombustible and easy to fix.

Area of application: Easy fixing of heavy loads up to 1.5 KN/m (150 kg/m wall length) just with screws.

## Technical specifications

Parameters	Sign	Value	Unit	Certification
Material				
Type of material		gypsum fibre		
Туре				
Туре		4B		EN 520
Building material class				
Fire behaviour		A2-s1, d0		EN 13501-1
Edges				
Longitudinal edge		T slot		
Transverse edge		SK		
Dimensions				
Thickness	t	20.0	mm	EN 520
Width	w	300	mm	EN 520
Length	1	610	mm	EN 14195
Heat				
Thermal conductivity	$\lambda_{_{R}}$	0.35	W/(m·K)	EN ISO 10456
	$\lambda_{\text{10,dry}}$	0.202	W/(m·K)	EN 12664

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.





## **Product data sheet**

Rigips pattressing

Parameters	Sign	Value	Unit	Certification
Notes				
Storage		Dry Flat and level Shady Cool		
Shelf Life		Unlimited		
Package Size		According to Pricelist		
Waste key number		17 08 02		

The values listed in this product data sheet only reflect the performance characteristics of the products. In addition, gypsum plaster systems have structural and structural properties, which can be found in our system documentation (e. g. Planen und Bauen).

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.

